

E70CC48 Product Data Sheet

Life Science applications



Ceetak is the leading provider of sealing solutions into the Life Sciences & Medical industry, providing technologically advanced materials, engineering expertise and high quality products.

Our unique portfolio of materials includes a broad range of elastomers formulated to satisfy the stringent material, production control and cleanliness regulations demanded by the industry.

Our advance production technologies and cleanroom facilities ensure we maintain the highest levels of quality assured product integrity .

E70CC48 is an EPDM compound for use in Life Sciences applications.

E70CC48 demonstrates excellent performance in water and steam application environments.


Basic Polymer: EPDM
Hardness: 70 +/- 5 Shore A
Temperature range: -50°C to +150°C
Colour: Black

Key features

- FDA approved
- ISO 10993-5 approved
- USP Class VI compliant

Production Methods

- Compression moulding
- Transfer moulding



Products

- O-Rings
- Gaskets
- Grommets

Property	Test	Units	Results
Hardness	ASTM D2240-05	Shore A	74.5
Tensile Strength	ASTM D412-06a	MPa	16
Elongation	ASTM D412-06a	%	190
Specific Gravity	D1817	g/cm ³	1.126
Compression Set	ASTM D395B 22Hrs @125°C	%	13
Modulus	ASTM D412-06a	MPa	5.52

Applications

- Medical Devices
- Valves
- Syringes
- Pumps
- Biomedical
- Pharmaceutical
- Filtration

These results represent typical material properties. They are achieved under laboratory conditions and do not necessarily correspond to results measured on finished goods. It does not absolve the customer of the responsibility to make tests for their intended process or purpose. Ceetak Ltd makes no warranties and assumes no liability in connection with any use of this information.



Registered in England: 2251723

Ceetak Ltd Head Office
 Fraser Road, Priory Business
 Park, Bedford, MK44 3WH
 www.ceetak.com
 Tel: 01234 832200

E: enquiries@ceetak.com

Ceetak Aberdeen
 Block 1, Unit 13, Souterhead
 Road, Altens Ind Est, Aberdeen,
 AB12 3LF
 Tel: 01224 249690

E: aberdeen@ceetak.com