

S70CK06 Product Data Sheet

Life Science applications



Ceetak is the leading provider of sealing solutions into the Life Sciences & Medical industry, providing technologically advanced materials, engineering expertise and high quality products.

Our unique portfolio of materials includes a broad range of elastomers formulated to satisfy the stringent material, production control and cleanliness regulations demanded by the industry.

Our advance production technologies and cleanroom facilities ensure we maintain the highest levels of quality assured product integrity .

S70CK06 is a peroxide cured, silicone elastomer compound for use in Life Sciences applications.

Silicone S70CK06 is recommended for its excellent performance in low and high temperature range environments, and various other application conditions required to meet and comply with USP Class VI.

Basic Polymer: Silicone
Hardness: 70 +/- 5 Shore A
Temperature range: -50°C to +200°C
Colour: Translucent

Key features

- USP Class VI approved
- ISO10993-5 approved
- ISO10993-10 approved
- ISO10993-11 approved
- FDA approved

Production Methods

- Compression moulding
- Transfer moulding



Products

- O-Rings
- Gaskets
- Grommets

Property	Test	Units	Results
Hardness	ASTM D2240-05	Shore A	73
Tensile Strength	ASTM D412-06A	MPa	10.64
Elongation	ASTM D412--06A	%	541
Specific Gravity	ASTM D297	g/cm ³	1.19
Tear Resistance	ASTM D624-00; Die B	KN/mm	28.23
Low Temperature	ASTM D2137-05 3 mins @ -55°C	%	Pass
Modulus	ASTM D412-06A	MPa	1.88

Applications

- Medical Devices
- Valves
- Syringes
- Pumps
- Biomedical
- Pharmaceutical
- Filtration

These results represent typical material properties. They are achieved under laboratory conditions and do not necessarily correspond to results measured on finished goods. It does not absolve the customer of the responsibility to make tests for their intended process or purpose. Ceetak Ltd makes no warranties and assumes no liability in connection with any use of this information.



Registered in England: 2251723

Ceetak Ltd Head Office
 Fraser Road, Priory Business
 Park, Bedford, MK44 3WH
 www.ceetak.com
 Tel: 01234 832200

E: enquiries@ceetak.com

Ceetak Aberdeen
 Block 1, Unit 13, Souterhead
 Road, Altens Ind Est, Aberdeen,
 AB12 3LF
 Tel: 01224 249690

E: aberdeen@ceetak.com