

FF200-75 Product Data Sheet

Oil & Gas applications

In conjunction with Parker Seals, this range of high performance materials for Oil & Gas meets the most challenging and demanding applications for aggressive chemicals, gas and high temperatures. These materials offer excellent chemical and thermal resistance and thermal stability under these extreme application conditions.

We provide our customers with the highest quality products and technical support on seal design, material recommendation, installation techniques and test analysis, specifically for the oil & gas market.

FF200-75 is an ultra high temperature FFKM. It is H₂S resistant NORSOK M-710 approved.

Basic Polymer: FFKM

Hardness: 75 +/- 5 Shore A

Temperature range: -15°C to +320°C

Colour: Black

Recommended for:

- Aliphatic and aromatic hydrocarbons
- Chlorinated hydrocarbons
- Polar solvents (acetone, methylethylketone, dioxane)
- Inorganic and organic acids
- Water and steam
- High vacuum with minimal loss in weight
- Petroleum oil
- Wet/dry chlorine

Original Physical Properties	Results
Hardness (Shore A)	79
Tensile Strength, MPa	12.0
Elongation, %, min.	124
Modulus @ 100% Elongation (MPa)	7.8
Compression Set (ASTM D395 Method B) %	45

Products

- O-rings

These results represent typical material properties. They are achieved under laboratory conditions and do not necessarily correspond to results measured on finished goods. It does not absolve the customer of the responsibility to make tests for their intended process or purpose. Ceetak Ltd makes no warranties and assumes no liability in connection with any use of this information.