

V1238-95 Product Data Sheet

Oil & Gas applications

In conjunction with Parker Seals, this range of high performance materials for Oil & Gas meets the most challenging and demanding applications for aggressive chemicals, gas and high temperatures. These materials offer excellent chemical and thermal resistance and thermal stability under these extreme application conditions.

We provide our customers with the highest quality products and technical support on seal design, material recommendation, installation techniques and test analysis, specifically for the oil & gas market.

V1238-95 FKM is ISO23936-2 RGD & H₂S 2%, NORSOK M-710 RGD and API6A FF/HH H₂S approved.

Basic Polymer: FKM
Hardness: 95 +/- 5 Shore A
Temperature range: -26°C to +204°C
Colour: Black

Recommended for:

- Mineral oil & grease
- IRM 901, IRM 902 & IRM903 oils
- Non-flammable hydraulic fluids
- Silicone oils & greases
- Aliphatic hydrocarbons
- Aromatic hydrocarbons
- Chlorinated hydrocarbons
- Gasoline
- High vacuum
- Ozone, weather & ageing resistance
- Rapid Gas Decompression

Original Physical Properties	Results
Hardness (Shore A)	94
Tensile Strength, MPa	21.10
Elongation, %, min.	98
Compression Set (70hrs @ 200°C) %	26
50% Modulus, MPa	9.90
Specific Gravity	1.83

Products

- O-rings
- Moulded shapes
- Back-up rings
- S-Seals
- PolyPaks®

These results represent typical material properties. They are achieved under laboratory conditions and do not necessarily correspond to results measured on finished goods. It does not absolve the customer of the responsibility to make tests for their intended process or purpose. Ceetak Ltd makes no warranties and assumes no liability in connection with any use of this information.