## FF400-80 Product Data Sheet Oil & Gas applications



In conjunction with Parker Seals, this range of high performance materials for Oil & Gas meets the most challenging and demanding applications for aggressive chemicals, gas and high temperatures. These materials offer excellent chemical and thermal resistance and thermal stability under these extreme application conditions.

We provide our customers with the highest quality products and technical support on seal design, material recommendation, installation techniques and test analysis, specifically for the oil & gas market.

FF400-80 is a FFKM with low temperature capabilities. It is tested and approved to TOTAL GS EP PVV142 and ISO 23936-2 RGD and  $\rm H_2S$  10%.

Basic Polymer: FFKM

Hardness: 80 +/- 5 Shore A

Temperature range: -40°C to +275°C

Colour: Black

## **Recommended for:**

- HTHP (High temperature/high pressure) applications
- · Lower temperature capabilities
- Cold storage conditions

	Original Physical Properties	Results
X	Hardness (Shore A)	82
X	Tensile Strength, MPa	11.56
	Elongation, %, min.	188
	Modulus @ 100% Elongation (MPa)	6.06
	Compression Set (70hrs @ 200°C) %	21
	Specific Gravity	1.85

## **Products**

- O-rings
- Moulded shapes

These results represent typical material properties. They are achieved under laboratory conditions and do not necessarily correspond to results measured on finished goods. It does not absolve the customer of the responsibility to make tests for their intended process or purpose. Ceetak Ltd makes no warranties and assumes no liability in connection with any use of this information.





## Ceetak Aberdeen

Block 1, Unit 13, Souterhead Road, Altens Ind Est, Aberdeen, AB12 3LF Tel: 01224 249690

E: aberdeen@ceetak.com

www.ceetak.com